

Test Report

宇鍾實業股份有限公司
411台中縣太平市永平路二段279號

報告號碼 : CE/2006/53872
日期 : 2006/05/18
頁數 : 1 of 2

以下測試樣品乃供應廠商所提供及確認：


樣品名稱 : 複合轉接頭
產品型號 : MAS
收件日期 : 2006/05/12.
測試日期 : 2006/05/12 TO 2006/05/18

測試結果

測試部位 NO.1 : 銀色金屬

測試項目	單位	測試方法	偵測極限值	結果
				NO.1
六價鉻	ppm	依照US EPA 3060A方法,用UV-VIS(US EPA 7196A)做分析	2	N.D.
鎘	ppm	依照 EN1122 方法B:2001或其他酸消化方法,用感應耦合電漿原子發射光譜儀(ICP-AES)做分析	2	45.0
汞	ppm	依照 US EPA 3052 方法或其他酸消化方法,用感應耦合電漿原子發射光譜儀(ICP-AES)做分析	2	N.D.
鉛	ppm	依照 US EPA 3050B 方法或其他酸消化方法,用感應耦合電漿原子發射光譜儀(ICP-AES)做分析	2	29809.7

- 備註：(1) N.D. = Not detected.($<$ MDL) / 未檢出(低於偵測極限值)
(2) ppm = mg/kg / 百萬分之一
(3) MDL= Method Detection Limit(偵測極限值)


Daniel Yeh, M.R. / Operation Manager
Signed for and on behalf of
SGS TAIWAN LTD.

Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful and offenders may be prosecuted to the fullest extent of the law.
對本報告內容或外觀之任何未經授權之變更、偽造、竄改皆屬非法，違犯者將會被依法追訴。

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf. Attention is drawn to the limitations of liability, indemnification, and Jurisdictional issues defined therein. The results shown in this test report refer only to the sample(s) tested unless otherwise stated. This Test Report cannot be reproduced, except in full, without prior written permission of the Company. 此報告是遵循本公司訂定之通用服務條款所製作發放。請注意此條款列印於背面，將本公司之義務，免責，管轄權皆明確規範之。此報告結果除非另有說明僅對檢驗之樣品負責。本報告未經本公司書面許可，不可部份複製。

TW 3257318

Test Report

宇鍾實業股份有限公司
411台中縣太平市永平路二段279號

報告號碼 : CE/2006/53872
日期 : 2006/05/18
頁數 : 2 of 2



Any unauthorized alteration, forgery or falsification of the content or appearance of this report is unlawful and offenders may be prosecuted to the fullest extent of the law.
對本報告內容或外觀之任何未經授權之變更、偽造、竄改皆屬非法，違犯者將會被依法追訴。

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf. Attention is drawn to the limitations of liability, indemnification, and Jurisdictional issues defined therein. The results shown in this test report refer only to the sample(s) tested unless otherwise stated. This Test Report cannot be reproduced, except in full, without prior written permission of the Company. 此報告是遵循本公司訂定之通用服務條款所製作發放。請注意此條款列印於背面，將本公司之義務，免責，管轄權皆明確規範之。此報告結果除非另有說明僅對檢驗之樣品負責。本報告未經本公司書面許可，不可部份複製。

TW 3257319

材質測試報告

NO :

REPORT OF MATERIAL TEST

Date :

客戶名稱 : 金田 Customer :	鋼 Copper	合金 Alloy	棒 Bars	交貨日期 : 95.05.10 Delivery Date :				
材質編號 : Material Alloy No.	C3600			交貨重量:153k Quantity :				
化學分析試驗 Chemical Analysis Test								
成分 Element	銅 Cu(%)	鉛 Pb(%)	鐵 Fe(%)	錫 Sn(%)	鎳 Ni(%)	鐵+錫 Fe+Sn(%)	鋅 Zn(%)	Rem
標準 Standard	60.0-63.0	2.5-3.7	<0.35	-	-	M<=1.5		
製令單號 Work No.	62.7093	2.5687	0.2288			0.4757		
產品尺寸 Size of product	9.5 圓							
機械物理試驗 Mechanical Physical Test								
試驗名稱 Item	尺寸試驗 Dimension Test		引張試驗 Tension Test		硬度試驗 Hardness Test			
	標準 Standard	長度公差(mm) Length	引張強度 N/mm2 Tensile Strength	伸長率 % Elongation	HV, HRB			
製令單號 Work No.	產品尺寸 Size of product							



Supervision :
管理部

QC :
品管

CE/2006/53872
材質表

